



Product Description:

A one component, high performance, paste-like sealant formulated to bond a variety of common construction materials. It has superior adhesion, outstanding durability, low shrinkage and adhere to most materials without the need for primer.

Applications:

Ideal for general sealing applications where only small amount of movement occurs. Well-suited for sealing applications for containers, roofs, external wall, window and door caulking etc. It also exhibits excellent adhesion to metal, wood, glass, zinc, slate, ceramic etc.

SPECIFICATION:

CURING SYSTEM	OXIDIZING
APPEARANCE	NON-SAGGING PASTE
ODOUR	MILD VUEGTABLE OILS
SPECIFIC GRAVITY	1.50 ± 0.30
MAX. JOINT MOVEMENT	±3%
SHRINKAGE	5 %
TACK FREE TIME	24 HOURS
APPLICATION TEMP.	4°C TO 50°C
SERVICE TEMP.	-5°C TO 60°C
SHELF LIFE	12 MONTHS

Directions:

Surfaces must be clean, dry and free of dirt, grease, oil or water.
Cut nozzle at 45° angle to desired bread-width and load into cartridge gun.
For a neat finish, apply masking tape and remove it before sealant has skinned over.
Use approved backing material for joints over 10mm deep.
Tooling time is 10 minutes, tack-free time is 24 hours.
Uncured sealant can be cleaned up with mineral spirit.

Safety and first aid directions:

Avoid contact with eyes, skin and mouth.
Use in well ventilated area. In case of contact with eyes, flush with water immediately for 15 minutes. If irritation persists, seek medical attention.
Keep out of reach of children.

Storage

Store in a dry and cool place with temperature below +25°C.
Use within 12 months from date of production.

Every endeavor has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of various of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.